

NobleSealant 150

Waterproofing Sealant and Seamer



- **Synthetic co-polymer rubber - high solids**
- **Excellent resistance to ozone, sunlight and weathering**
- **Unaffected by exposure to water after cured**
- **Adheres to wood, metal, concrete, glass, plastic & rubber**
- **Broad temperature use range (-65°F to 122°F)**
- **Three-year shelf life at room temperature if unopened**
- **Applications:**
 - seam membrane sheets together
 - seal penetrations of the membrane
 - provide a seal between the waterproof membrane and clamping ring drain
 - as a concealed terminal edge and flashing sealant
 - adhere preformed corners to the waterproofing membrane, studs, etc.
 - spot bond sheet to vertical or horizontal surfaces



Characteristics

Elastomer Base:	Thermoplastic Elastomer
Color:	Light Blue
Contents:	10.3 Fluid Ounces
Spread Rates:	40 l.f. with 3/16" bead

Note:

Surface must be clean, dry and free of dust, oil and grease.
Use a heavy-duty commercial caulking gun.

CAUTION: Contains propylacetate. Store below 85°F.
Avoid prolonged contact with skin or inhalation of vapors.
Use with adequate ventilation.

Penetrations: Patch penetration with a piece of membrane approximately 2" larger on all sides that the penetration.
Seal patch over penetration with a 3/16" bead of NobleSealant 150.
Use enough NobleSealant 150 to insure water-tightness.

Curing: Times for curing can vary from 30 minutes to 24 hours depending on a variety of conditions (e.g. temperature, humidity, air flow, etc.). Allowing seams to cure overnight is recommended.

Sheet Membrane Seaming/Joining



Seaming:

1. Overlap sheets approximately 2".
(Note: Polyester fabric does not need to be removed.)
2. Apply a 3/16" bead of NobleSealant 150.
(Note: Beads must be parallel and continuous without voids or skips.)
3. To seal, press overlapped sheets together and use a trowel or hand roller to flatten bead.